

# Faktis F 14

## Brown Sulphur Factice

### Description

Brown sulphur factice, free of mineral oil

### Composition

Rapeseed oil, cross-linked with sulphur

### Application

For coloured and black articles based on general purpose rubbers, especially extruded sections

### Dosage

10 – 30 phr, depending on the application

### Typical physical properties

		Unit
Colour	Small brown lumps	/
Total sulphur	14.5 – 17.5	%
Free sulphur	0.4 – 0.9	%
Acetone extract	approx. 18	%
Ash, 2h at 950°C	max. 0.2	%
Density at 20°C	1.1	g/cm <sup>3</sup>

### Benefits

Broad range of application  
Also available finely ground  
Mainly for extrudates, printing blankets or rollers  
BfR / FDA suitable

### Associated products

F 10  
F 17  
F 25  
F 10 soft  
DS soft  
K 14 D  
PD 14  
NP 17

### Storage

In originally sealed package in cool and dry places  
Storage stability: min. 18 months

### Supply Form

25 kg in PE-bags

### German Food Legislation (BfR recommendation XXI)

Approved

### US Code of Federal Regulations, FDA – CFR Title 21, 177.2600

Listed

Version: 01/2022