

Faktis NP 17

Brown Sulphur Factice

Description

Brown sulphur factice, free of mineral oil

Composition

Rapeseed oil and special oils, cross-linked with sulphur

Application

For articles based on CR when mineral oil is used as softener. It is applicable for all cases where sewing resistance is not the main point i.e. when castor oil factices are not required. Factice NP 17 improves the ozone resistance of CR vulcanizates

Dosage

10 – 30 phr, depending on the application

Typical physical properties

		Unit
Colour	Small, light brown lumps	/
Total sulphur	11.5 – 14.5	%
Free sulphur	0.1 – 0.6	%
Acetone extract	approx. 38	%
Ash, 2h at 950°C	max. 0.2	%
Density at 20°C	1.0	g/cm ³

Benefits

Mainly used for CR
Reduced mill sticking
Good dispersibility

Associated products

F 14
F 17
F 25
F 10
F 10 soft
DS soft
K 14 D
PD 14

Storage

In originally sealed package in cool and dry places at max. 25°C
Storage stability: min. 12 months

Supply Form

25 kg in PE-bags

German Food Legislation (BfR recommendation XXI)

Not approved

US Code of Federal Regulations, FDA – CFR Title 21, 177.2600

Not listed

Version: 01/2022