
# Faktis WP Peroxide Factice



# Composition

Modified castor oil, cross-linked with peroxide

## **Application**

For heat resistant articles based on special elastomers for all kinds of cross-linking, especially for peroxide curing. There is no negative influence of factice WP on the compression set even at higher dosage levels

#### Dosage

5 - 15 phr, depending on the application

# **Typical physical properties**

		Unit
Colour	White ground product	/
Acetone extract	approx. 18	%
Ash, 2h at 950°C	max. 0.2	%
Density at 20°C	1.0	g/cm³

#### Benefits

For all vulcanization types, particularly peroxide curing No influence on compression set Excellent heat- and UV-resistance Suitable for transparent articles

## **Associated products**

WPF-NT

#### Storage

In originally sealed package in cool and dry places Storage stability: min. 24 months

#### **Supply Form**

25 kg in PE-bags

## German Food Legislation (BfR recommendation XXI)

Not approved

US Code of Federal Regulations, FDA – CFR Title 21, 177.2600 Not listed

Version: 01/2022



DOG DEUTSCHE OELFABRIK Gesellschaft für chemische Erzeugnisse mbH & Co. KG

Ellerholzdamm 50 · 20457 Hamburg/Germany Tel. + 49 40 3118050 Fax + 49 40 31180588 info@dog-chemie.de · www.dog-chemie.de The data in this document has been compiled to the best of our knowledge. However, the product may not be suitable for all applications and working environments. Liability or warranty is therefore expressly excluded.

